

Rhenogran® CUT-50

Predispersed rubber chemicals and additives

Function

Special accelerator for the vulcanization of EPDM and other diene rubbers

Product description

| | |
|---------------------------|--|
| Composition: | 50 % copper dithiophosphate 50 % polymer binder and fillers |
| Appearance: | dark green granules |
| Density, 20 °C: | approx. 1.3 g/cm ³ |
| Physiological properties: | see safety data sheet |

Use

| | |
|-----------------|--|
| Mode of action: | In combination with sulfur and secondary accelerators, e.g. of the thiazole and the thiuram class, Rhenogran CUT-50 provides a very rapid and scorch-safe crosslinking of EPDM. Vulcanizates with a high degree of crosslinking and aging resistance as well as a good compression set are obtained. |
| Processing: | The thermoplastic, fully compatible polymer binder, which is combined with special dispersing agents, allows quick absorption and excellent dispersion in the rubber. In this way, optimal activity of the effective substance is assured. Due to the coarse-grain nature of the raw material crystallites may occasionally occur. Therefore, mixing temperature and time have to be adjusted accordingly. |
| Dosage: | 0.5 - 3.0 phr. Dosages up to about 1 phr normally cause no discoloration, at higher dosages and in contact with PVC slightly brown discoloration may occur. |
| Application: | Molded and extruded technical articles, e.g. profiles, foils, damping elements, dock fenders |

Packaging

20 kg carton with PE bag inside on 960 kg skid

Storage stability

In closed original containers under cool and dry conditions 730 days from date of production

Handling

For additional handling information on Rhenogran CUT-50 please consult current safety data sheet

Our technical advice - whether verbal, in writing or by way of trials - is given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. It does not release you from the obligation to test the products supplied by us as to their suitability for the intended processes and uses. The application, use and processing of the products are beyond our control and, therefore, entirely your own responsibility. Should, in spite of this, liability be established for any damage, it will be limited to the value of the goods delivered by us and used by you. We will, of course, provide products of consistent quality within the scope of our General Conditions of Sale and Delivery.



LANXESS Deutschland GmbH
Business Unit Rhein Chemie
Kennedyplatz 1
D-50569 Cologne, Germany
<http://rch.lanxess.com>